

## **REPORT No.: 010 – M – 2013**

concerning mortar tests

### **1 Basic specification**

Customer:	<b>IZONIL GROUP s.r.o.</b> Svätopeterská 7/3064, 947 01 Hurbanovo
Indication of tested material:	<b>IZONIL CEMENT</b>
Number of sample:	357/MCT/2/2013
Date of sample reception:	02. 10. 2013
Date of testing:	02. 10. 2013 - determination of consistence and manufacturing of tested bodies 30. 10. 2013 - flexural strength and compressive strength of hardened mortar in 28 days 04. 11. - 13. 11. 2013 - capillary action of hardened mortar 19. 11. - 20. 11. 2013 - capillary of hardened mortar
Tested by:	Helena Bognárová, Jozef Varga
Type of test:	type-testing

#### **1.1 Test standards, prescription of testing procedure**

- STN EN 1015-2 Methods of tests for mortar for masonry. Part 2: Bulk sampling of mortars and preparation of test mortars (72 2441)
- STN EN 1015-3 Methods of tests for mortar for masonry. Part 3: Determination of consistence of fresh mortar (by flow table) (72 2441)
- STN EN 1015-11 Methods of tests for mortar for masonry. Part 11: Determination of flexural and compressive strength of hardened mortar (72 2441)
- STN EN 1015-18 Methods of tests for mortar for masonry. Part 18: Determination of water absorption coefficient due to capillary action of hardened mortar (72 2441)

